

## PROPERTIES AND APPLICATIONS

TESNIT® BA-S is a gasket material with good chemical and mechanical properties, resistance to oils, fuels and cooling fluids. TESNIT® BA-S is recommended for the chemical, petro-chemical, construction, automotive and OEM industries such as compressor and diesel engine applications.

Composition	Aramid fibers, NBR		
Colour	Green		
Approvals	Please inquire.		


## TECHNICAL DATA

Typical values for a thickness of 2 mm

<b>Density</b>	DIN 28090-2	g/cm <sup>3</sup>	1.8
<b>Compressibility</b>	ASTM F36J	%	8
<b>Recovery</b>	ASTM F36J	%	60
<b>Tensile strength</b>	ASTM F152	MPa	13
<b>Stress resistance</b>	DIN 52913		
16 h, 50 MPa, 175 °C		MPa	26
16 h, 50 MPa, 300 °C		MPa	20
<b>Specific leak rate</b>	DIN 3535-6	mg/(s·m)	0.05
<b>Thickness increase</b>	ASTM F146		
Oil IRM 903, 5 h, 150 °C		%	4
ASTM Fuel B, 5 h, 23 °C		%	6
<b>Compression modulus</b>	DIN 28090-2		
At room temperature: $\epsilon_{KSW}$		%	/
At elevated temperature: $\epsilon_{WSW/200\text{ °C}}$		%	/
<b>Percentage creep relaxation</b>	DIN 28090-2		
At room temperature: $\epsilon_{KRW}$		%	/
At elevated temperature: $\epsilon_{WRW/200\text{ °C}}$		%	/
<b>Max. operating conditions</b>			
Peak temperature		°C/°F	330/662
Continuous temperature		°C/°F	250/482
- with steam		°C/°F	200/392
Pressure	bar/psi		100/1450

## P-T DIAGRAM

EN 1514-1, Type IBC, PN 40, DIN 28091-2 / 3.8, 2.0 mm




- General suitability applying common installation practices under the condition of chemical compatibility.
- Maximum performance is ensured through appropriate measures for joint design and gasket installation. Consultation is recommended.
- Limited application area. Technical consultation is mandatory.

Surface finish	Surface finish is 2AS. Optional graphite or PTFE finish on request.
Dimensions of standard sheets	Sheet size [mm]: 1500 x 1500 Thickness [mm]: 0.5   1.0   1.5   2.0   3.0 Other dimensions and thicknesses are available on request.
Tolerances	± 5 % on length and width On thickness up to 1.0 mm ± 0.1 mm On thickness above 1.0 mm ± 10 %

Acetamide	+
Acetic acid, 10%	+
Acetic acid, 100% (Glacial)	?
Acetone	?
Acetonitrile	-
Acetylene [gas]	+
Acid chlorides	-
Acrylic acid	?
Acrylonitrile	-
Adipic acid	+
Air [gas]	+
Alcohols	+
Aldehydes	?
Alum	+
Aluminum acetate	+
Aluminum chloride	?
Aluminum chloride	?
Aluminum sulfate	?
Amines	-
Ammonia [gas]	?
Ammonium bicarbonate	+
Ammonium chloride	+
Ammonium hydroxide	+
Amyl acetate	?
Anhydrides	?
Aniline	-
Anisole	?
Argon [gas]	+
Asphalt	+
Barium chloride	+
Benzaldehyde	-
Benzene	+
Benzoic acid	?
Bio-diesel	+
Bio-ethanol	+
Black liquor	?
Borax	+
Boric acid	+
Butadiene [gas]	+
Butane [gas]	+
Butyl alcohol [Butanol]	+
Butyric acid	+
Calcium chloride	+
Calcium hydroxide	+
Carbon dioxide [gas]	+
Carbon monoxide [gas]	+
Cellosolve	?
Chlorine [gas]	-
Chlorine [in water]	-
Chlorobenzene	-
Chloroform	-
Chloroprene	?
Chlorosilanes	-
Chromic acid	-
Citric acid	?
Copper acetate	+
Coppersulfate	+
Cresote	?
Cresols [Cresylic acid]	-
Cyclohexane	+
Cyclohexanol	+
Cyclohexanone	?
Decalin	+
Dextrin	+
Dibenzyl ether	?
Diethyl phthalate	?
Dimethylacetamide [DMA]	?
Dimethylacetamide [DMA]	?
Dimethylformamide [DMF]	?
Dioxane	-
Diphyl [Dowtherm A]	+
Esters	?
Ethane [gas]	+
Ethers	?
Ethyl acetate	?
Ethyl alcohol [Ethanol]	+
Ethyl cellulose	?
Ethyl chloride [gas]	-
Ethylene [gas]	+
Ethylene glycol	+
Formaldehyde [Formalin]	?
Formamide	?
Formic acid, 10%	+
Formic acid, 85%	?
Formic acid, 100%	-
Freon-12 IR-121	?
Freon-134a IR-134a	?
Freon-22 IR-22	?
Fruit juices	+
Fuel oil	+
Gasoline	+
Gelatin	+
Glycerine [Glyceroll]	+
Glycols	+
Helium [gas]	+
Heptane	+
Hydraulic oil [Glycol based]	+
Hydraulic oil [Mineral type]	+
Hydraulic oil [Phosphate ester based]	?
Hydrazine	-
Hydrochloric acid, 10%	?
Hydrochloric acid, 37%	-
Hydrofluoric acid, 10%	-
Hydrofluoric acid, 48%	-
Hydrogen [gas]	+
Iron sulfate	+
Isobutane [gas]	+
Iso-octane	+
Isoprene	+
Isopropyl alcohol [Isopropanol]	+
Kerosene	+
Ketones	?
Lactic acid	?
Lead acetate	+
Lead arsenate	+
Magnesium sulfate	+
Maleic acid	?
Malic acid	?
Methane [gas]	+
Methyl alcohol [Methanol]	+
Methyl chloride [gas]	?
Methylene dichloride	?
Methyl ethyl ketone [MEK]	?
N-Methyl-pyrrolidone [NMP]	?
Milk	+
Mineral oil [ASTM no.1]	+
Motor oil	+
Naphtha	+
Nitric acid, 10%	?
Nitric acid, 65%	-
Nitrobenzene	-
Nitrogen [gas]	+
Nitrous gases [NOx]	?
Octane	+
Oils [Essential]	+
Oils [Vegetable]	+
Oleic acid	+
Oleum [Sulfuric acid, fuming]	-
Oxalic acid	?
Oxygen [gas]	?
Palmitic acid	+
Paraffin oil	+
Pentane	+
Perc-Horoethylene	-
Petroleum [Crude oil]	+
Phenol [Carboxylic acid]	-
Phosphoric acid, 40%	?
Phosphoric acid, 85%	-
Phthalic acid	+
Potassium acetate	+
Potassium bicarbonate	+
Potassium carbonate	+
Potassium chloride	+
Potassium cyanide	+
Potassium dichromate	?
Potassium hydroxide	?
Potassium iodide	+
Potassium nitrate	+
Potassium permanganate	?
Propane [gas]	+
Propylene [gas]	+
Pyridine	-
Salicylic acid	?
Seawater/brine	+
Silicones [oil/grease]	+
Soaps	+
Sodium aluminate	+
Sodium bicarbonate	+
Sodium bisulfite	+
Sodium carbonate	+
Sodium chloride	+
Sodium cyanide	+
Sodium hydroxide	?
Sodium hypochlorite [Bleach]	?
Sodium silicate [Water glass]	+
Sodium sulfate	+
Sodium sulfide	+
Starch	+
Steam	+
Stearic acid	+
Styrene	?
Sugars	+
Sulfur	?
Sulfur dioxide [gas]	?
Sulfuric acid, 20%	-
Sulfuric acid, 98%	-
Sulfuryl chloride	-
Tar	+
Tartaric acid	?
Tetrahydrofuran [THF]	-
Titanium tetrachloride	-
Toluene	+
2,4-Toluenediisocyanate	?
Transformer oil [Mineral type]	+
Trichloroethylene	-
Vinegar	+
Vinyl chloride [gas]	-
Vinylidene chloride	-
Water	+
White spirits	+
Xylenes	+
Xylenol	-
Zinc sulfate	+

## σ<sub>BO</sub> DIAGRAM

DIN 28090-1



σ<sub>BO</sub> diagrams represent σ<sub>BO</sub> values for different gasket material thicknesses. These values indicate the maximum in-service compressive pressures which can be applied on the gasket area involved without destroying or damaging the gasket material.

**P-T diagrams** indicate the maximum allowed combination of internal pressure and service temperature which can be applied simultaneously for a given gasket depending on its material type, thickness, size and tightness class. Given the variety of gasket applications and service conditions, these values should only be regarded as guidance for the proper gasket assembly. In general, thinner gaskets exhibit better P-T properties.

## CHEMICAL RESISTANCE CHART

The recommendations made here are intended as a guideline for the selection of the suitable gasket type. As the function and durability of the products is dependent upon a number of factors, the data may not be used to support any warranty claims.

⊕ Recommended

⊕ Recommendation depends on operating conditions

- Not recommended

**TT GASKETS**  
TAMPEREEN TIIVISTETEOLLISUUS



[www.tt-gaskets.fi/en/](http://www.tt-gaskets.fi/en/)



+358 3 358 1500



[sales@tt-gaskets.fi](mailto:sales@tt-gaskets.fi)



Alasniitynkatu 14,  
33560 Tampere-Finland